

Valspar SR Roof Products Listed with Energy Star 2008

Brand	Model	Type	Initial Solar Reflectance	3-Year Solar Reflectance	Initial Emittance	Low Slope	Steep Slope
Fluropon SR	Aged Copper	Coating	.47	.46	.85	N	Y
Fluropon SR	Almond	Coating	.57	.56	.86	N	Y
Fluropon SR	Almonde	Coating	.60	.57	.84	N	Y
Fluropon SR	Antique Patina	Coating	.29	.30	.87	N	Y
Fluropon SR	Apothecary Blue	Coating	.26	.26	.85	N	Y
Fluropon SR	Arcadia Green	Coating	.34	.33	.88	N	Y
Fluropon SR	Artic White	Coating	.56	.55	.84	N	Y
Fluropon SR	Ash Gray	Coating	.39	.39	.85	N	Y
Fluropon SR	Beige	Coating	.40	.39	.86	N	Y
Fluropon SR	Banner Red	Coating	.42	.41	.84	N	Y
Fluropon SR	Birch White	Coating	.64	.65	.85	N	Y
Fluropon SR	Bone White	Coating	.72	.70	.84	Y	Y
Fluropon SR	Brandywine	Coating	.25	.23	.85	N	Y
Fluropon SR	Brick Red	Coating	.29	.29	.87	N	Y
Fluropon SR Classic II	Bright Copper	Coating	.49	.47	.85	N	Y
Fluropon SR	Bright Silver	Coating	.59	.60	.80	N	Y
Fluropon SR	Brite Red	Coating	.32	.34	.79	N	Y
Fluropon SR	Brownstone	Coating	.38	.38	.85	N	Y

For the most current
list, please visit
www.energystar.gov



valspar

VAL392
090825
Page 1 of 1

Valspar SR Roof Products Listed with Energy Star 2008

Brand	Model	Type	Initial Solar Reflectance	3-Year Solar Reflectance	Initial Emittance	Low Slope	Steep Slope
Fluropon SR	Burgundy	Coating	.25	.23	.85	N	Y
Fluropon SR	Champagne	Coating	.37	.36	.83	N	Y
Fluropon SR	Champagne Gold	Coating	.48	.48	.85	N	Y
Fluropon SR	Champagne Pearl	Coating	.48	.48	.81	N	Y
Fluropon SR	Charcoal Gray	Coating	.27	.26	.85	N	Y
Fluropon SR	Chromium Gray	Coating	.48	.44	.85	N	Y
Fluropon SR	City Scape	Coating	.37	.34	.85	N	Y
Fluropon SR	Classic Green	Coating	.27	.26	.83	N	Y
Fluropon SR	Clay	Coating	.33	.32	.85	N	Y
Fluropon SR	Colonial Red	Coating	.27	.23	.85	N	Y
Fluropon SR Low Gloss	Colonial Red	Coating	.35	.32	.86	N	Y
Fluropon SR	Cool Brite Red	Coating	.44	.43	.84	N	Y
Fluropon SR	Cool Copper Penny	Coating	.44	.41	.81	N	Y
Fluropon SR	Copper Metallic	Coating	.45	.44	.85	N	Y
Fluropon SR	Copper Penny	Coating	.43	.42	.83	N	Y
Fluropon SR	Coronado Red	Coating	.38	.37	.84	N	Y
Fluropon SR Low Sheen	Dark Bronze	Coating	.26	.25	.85	N	Y
Fluropon SR	Dark Bronze	Coating	.26	.25	.84	N	Y

For the most current
list, please visit
www.energystar.gov



valspar

VAL392
090825
Page 2 of 2

Valspar SR Roof Products Listed with Energy Star 2008

Brand	Model	Type	Initial Solar Reflectance	3-Year Solar Reflectance	Initial Emittance	Low Slope	Steep Slope
Flurospar SR	Desert Beige	Coating	.35	.34	.86	N	Y
Fluropon SR	Egyptian White	Coating	.54	.53	.85	N	Y
Fluropon SR	Granite	Coating	.36	.35	.84	N	Y
Fluropon SR	Hemlock Green	Coating	.34	.33	.86	N	Y
Fluropon SR	Herringbone	Coating	.63	.63	.86	N	Y
Fluropon SR	Ivory	Coating	.67	.65	.87	Y	Y
Fluropon SR Low Gloss	Jade Green	Coating	.29	.29	.85	N	Y
Fluropon SR	Khaki	Coating	.42	.42	.85	N	Y
Fluropon SR	Lee Ivory	Coating	.64	.62	.85	N	Y
Fluropon SR	Light Gray	Coating	.54	.55	.85	N	Y
Fluropon SR	Light Seawolf	Coating	.39	.40	.86	N	Y
Fluropon SR	Light Stone	Coating	.50	.50	.87	N	Y
Fluropon SR	Limestone	Coating	.56	.55	.84	N	Y
Fluropon SR	Linen White	Coating	.72	.71	.84	Y	Y
Flurpon SR	Mansard Brown	Coating	.30	.29	.85	N	Y
Fluropon SR Low Gloss	Marine Green	Coating	.35	.35	.85	N	Y
Fluropon SR	Matte Black	Coating	.27	.27	.86	N	Y
Fluropon SR	Metallic Silver	Coating	.60	.60	.77	N	Y

For the most current
list, please visit
www.energystar.gov



valspar

VAL392
090825
Page 3 of 3

Valspar SR Roof Products Listed with Energy Star 2008

Brand	Model	Type	Initial Solar Reflectance	3-Year Solar Reflectance	Initial Emittance	Low Slope	Steep Slope
Fluropon SR	Moss	Coating	.28	.28	.86	N	Y
Fluropon SR	Musket Gray	Coating	.32	.31	.84	N	Y
Fluropon SR	Natural Patina	Coating	.39	.39	.85	N	Y
Fluropon SR	Off White	Coating	.71	.67	.85	Y	Y
Fluropon SR Low Gloss	Old Town Gray	Coating	.26	.26	.86	N	Y
Fluropon SR	Patina Green	Coating	.26	.28	.88	N	Y
Fluropon SR	Patriot Red	Coating	.42	.41	.84	N	Y
Fluropon SR Classic II	Pewter	Coating	.31	.27	.86	N	Y
Fluropon SR	Polar White	Coating	.65	.64	.86	Y	Y
Fluropon SR	Portland Stone	Coating	.45	.44	.85	N	Y
Fluropon SR	Rawhide	Coating	.53	.51	.86	N	Y
Fluropon SR	Regal Blue	Coating	.26	.25	.85	N	Y
Fluropon SR	Regal Gray	Coating	.44	.44	.84	N	Y
Fluropon SR	Regal Red	Coating	.36	.36	.83	N	Y
Fluropon SR	Regal White	Coating	.68	.67	.86	Y	Y
Fluropon SR	Regal White	Coating	.70	.68	.84	Y	Y
Fluropon SR	Ruby Red	Coating	.40	.34	.82	N	Y
Fluropon SR	Sahara Tan	Coating	.41	.39	.86	N	Y

For the most current
list, please visit
www.energystar.gov



valspar

VAL392
090825
Page 4 of 4

Valspar SR Roof Products Listed with Energy Star 2008

Brand	Model	Type	Initial Solar Reflectance	3-Year Solar Reflectance	Initial Emittance	Low Slope	Steep Slope
Fluropon SR	Sandstone	Coating	.51	.50	.85	N	Y
Fluropon SR	Sandstone Metallic	Coating	.47	.46	.80	N	Y
Fluropon SR	Sandstone SR	Coating	.54	.55	.85	N	Y
Fluropon SR	Scarlet Red	Coating	.34	.39	.85	N	Y
Fluropon SR	Seal Brown	Coating	.31	.31	.87	N	Y
Fluropon SR	Shelburne	Coating	.69	.68	.85	Y	Y
Fluropon SR	Sierra Gold	Coating	.47	.46	.86	N	Y
Fluropon SR	Sierra Tan	Coating	.35	.34	.86	N	Y
Fluropon SR	Sierra Tan	Coating	.38	.38	.86	N	Y
Fluropon SR	Sierra White	Coating	.72	.69	.85	Y	Y
Fluropon SR	Silver Gray	Coating	.29	.26	.86	N	Y
Fluropon SR	Silver Metal	Coating	.55	.53	.79	N	Y
Fluropon SR	Silver Metallic	Coating	.59	.60	.80	N	Y
Fluropon SR	Slate Blue	Coating	.29	.28	.85	N	Y
Fluropon SR	Slate Gray	Coating	.40	.40	.85	N	Y
Fluropon SR	Snowdrift White	Coating	.62	.61	.84	N	Y
Fluropon SR	Spruce	Coating	.28	.29	.86	N	Y
Fluropon SR	Stone White	Coating	.60	.56	.86	N	Y

For the most current list, please visit www.energystar.gov



valspar

VAL392
090825
Page 5 of 5

Valspar SR Roof Products Listed with Energy Star 2008

Brand	Model	Type	Initial Solar Reflectance	3-Year Solar Reflectance	Initial Emittance	Low Slope	Steep Slope
Fluropon SR	Surrey Beige	Coating	.42	.41	.85	N	Y
Fluropon SR	Taupe	Coating	.30	.29	.85	N	Y
Fluropon SR	Teal Patina	Coating	.37	.37	.86	N	Y
Fluropon SR	Terra Cotta	Coating	.35	.35	.87	N	Y
Fluropon SR	Tundra	Coating	.34	.34	.85	N	Y
Fluropon SR Classic II	Zinc	Coating	.51	.49	.79	N	Y
WeatherX SR	Alamo White	Coating	.64	.62	.85	N	Y
WeatherX SR	Ash Gray	Coating	.48	.47	.87	N	Y
WeatherX SR	Autumn Red	Coating	.35	.32	.85	N	Y
WeatherX SR	Aztec Gold	Coating	.53	.53	.86	N	Y
WeatherX SR	Blue	Coating	.25	.25	.86	N	Y
WeatherX SR	Brite Red	Coating	.38	.32	.86	N	Y
WeatherX SR	Brite White	Coating	.71	.68	.85	Y	Y
WeatherX SR	Burgundy	Coating	.26	.27	.84	N	Y
WeatherX SR	Colony Green	Coating	.36	.35	.87	N	Y
WeatherX SR	Crimson Red	Coating	.33	.32	.85	N	Y
WeatherX SR	Crimsons Red	Coating	.38	.32	.86	N	Y
WeatherX SR	Crystal White	Coating	.65	.64	.85	Y	Y

For the most current list, please visit www.energystar.gov



valspar

VAL392
090825
Page 6 of 6

Valspar SR Roof Products Listed with Energy Star 2008

Brand	Model	Type	Initial Solar Reflectance	3-Year Solar Reflectance	Initial Emittance	Low Slope	Steep Slope
WeatherX SR	Dark Brown	Coating	.26	.22	.87	N	Y
WeatherX SR	Desert Tan	Coating	.66	.65	.85	Y	Y
WeatherX SR	Desert Sand	Coating	.42	.36	.87	N	Y
WeatherX SR	Evergreen	Coating	.28	.22	.84	N	Y
WeatherX SR	Forest Green	Coating	.28	.22	.84	N	Y
WeatherX SR	Gallery Blue	Coating	.29	.30	.86	N	Y
WeatherX SR	Glossy White	Coating	.71	.72	.85	Y	Y
WeatherX SR	Gold	Coating	.47	.48	.86	N	Y
WeatherX SR	Hawaiian Blue	Coating	.25	.20	.86	N	Y
WeatherX SR	High Gloss White	Coating	.71	.72	.85	Y	Y
Weather X SR	Ivory	Coating	.66	.65	.85	Y	Y
WeatherX SP	Light Brown	Coating	.25	.25	.86	N	Y
WeatherX SR	Light Gray	Coating	.42	.36	.87	N	Y
WeatherX SR	Light Stone	Coating	.50	.50	.87	N	Y
WeatherX SR	Pewter Gray	Coating	.32	.25	.85	N	Y
WeatherX SR	Polar White	Coating	.60	.59	.85	N	Y
WeatherX SR	Red	Coating	.28	.24	.85	N	Y
WeatherX SR	Roman Blue	Coating	.32	.29	.85	N	Y

For the most current
list, please visit
www.energystar.gov



valspar

VAL392
090825
Page 7 of 7

Valspar SR Roof Products Listed with Energy Star 2008

Brand	Model	Type	Initial Solar Reflectance	3-Year Solar Reflectance	Initial Emittance	Low Slope	Steep Slope
WeatherX SR	Rustic Red	Coating	.36	.35	.86	N	Y
WeatherX SR	Saddle Tan	Coating	.48	.47	.87	N	Y
WeatherX SR	Tan	Coating	.41	.37	.86	N	Y
WeatherX SR	Taupe	Coating	.38	.38	.87	N	Y
WeatherX SR	USDA White	Coating	.61	.64	.85	N	Y

For the most current
list, please visit
www.energystar.gov



valspar

VAL392
090825
Page 8 of 8