



www.paintandcolor.com

WeatherX™ silicone polyester coatings are resistant to many elements found in the environment such as air pollution, acid rain and general airborne dirt. However, if the need to clean or remove deposits from your coating does arise, a variety of methods for removal of surface deposits are available. Two precautions: (1) do not use wire, brushes, abrasives or similar cleaning tools which will mechanically abrade the coatings surface, and (2) certain cleaning agents listed below should be tested in an inconspicuous area before use on a large scale.

GROUP A: HOT OR COLD DETERGENT SOLUTIONS

A 5% solution in water of commonly used commercial (non-industrial) detergents will not have any deleterious effect on a painted surface. These solutions should be followed by an adequate rinse of water. Use a cloth or a soft bristle brush for application.

GROUP B: SOLVENTS

Most organic solvents are flammable and/or toxic, and must be handled accordingly.

Read the manufacturer's Material Safety Data Sheet (MSDS) on solvent used. Keep away from open flames, sparks and electrical motors. Use adequate ventilation, protective clothing and goggles.

Solvents that may be used to remove on-water soluble deposits such as tar, grease, oil, paint and graffiti from Coil Clad 10S and WeatherX surfaces include:

Alcohols

- Denatured alcohol (ethanol)
- Isopropyl (rubbing alcohol)

The above alcohols have no permanent effect on Coil Clad 10S and WeatherX surfaces.

GROUP C: PETROLEUM SOLVENTS AND TURPENTINE

- VM&P naphtha
- Mineral spirits
- Kerosene
- Turpentine (wood or gum spirits)

The above solvents have no permanent effect on Coil Clad 10S and WeatherX surfaces.

GROUP D: AROMATIC AND CHLORINATED

- Xylol (Xylene)
- Toluol (Toluene)

The above solvents should be used with caution on a silicone polyester surface. Limit contact of the Coil Clad 10S and WeatherX surfaces with solvent to five minutes maximum and test before using.

GROUP E: KETONES, ESTERS, LACQUER THINNER AND PAINT REMOVER

- Methyl isobutyl ketone (MIBC)
- Ethyl acetate nail polish remover)
- Butyl acetate
- Lacquer thinner
- Paint remover

The above solvents should not be used on a Coil Clad 10S or WeatherX surface.

GRAFFITI

Graffiti presents a special problem because of the many possible agents used, generally aerosol paint. It is best to try soap and water first, then the solvents. If none of these are satisfactory it may be necessary to resort to touchup, repaint or replacement.

WARRANTY

Misuse or abuse of any of any of the cleaning agents listed above will result in a voiding of warranty for the surface affected.

For more information, contact Valspar's Coil or Extrusion Coatings Division:

901 North Greenwood Ave • Kankakee, IL USA 60901 • FAX: 815.936.7811 • Telephone: 815.933.5561 or 888.306.2645
701 South Shiloh Road • Garland, TX USA 75042-7812 • FAX: 972.487.7245 • Telephone: 972.276.5181 or 800.406.6480
347 Central Avenue • Bowling Green, KY USA 42101 • FAX: 502.746.6815 • Telephone: 270.843.4831 or 800.762.2626
645 Coronation Dr • West Hill, Ontario Canada M1E 4R6 • FAX: 416.284.6549 • Telephone: 416.284.1681 or 800.268.4277
Avenue Central 223 Los Lornas • Guadalupe, N.L. Mexico 67190 • Telephone: 52818.360.2020



www.paintandcolor.com

Val#220
080510
©The Valspar Corporation
All Rights Reserved